

Brady B-3 Floor Marking Tape

TDS No. B-3

Effective Date: 05/11/2020

Description:

Brady B-3 is a vinyl floor marking tape with good durability and adhesive. It is made of a sturdy vinyl that makes it easier to lay down in straight lines.

Use:

Brady B-3 is used to mark aisles, passageways, storage locations, and exits. For use in typical foot traffic areas.

Adhesive Type:

Permanent acrylic pressure-sensitive adhesive.

Substrate Type:

Vinyl

Standard Material Colors:

Solid: white, red, yellow, green, blue, orange, black, gray, brown, clear, and purple

Thickness:

0.004 in.

Adhesive Properties:

Adhesion to Steel (PSTC-101)

15 Minute Dwell (Avg.) -- 80 oz/in. (87.5 N/100mm)

Ultimate Dwell (72 Hrs.) 85 oz/in. (93 N/100mm)

Tack (ASTM D 2979) (Avg.) 1100 g (10.5 N)

Adhesion to Powder Coated Metal (PSTC-101)

15 Minute Dwell (Avg.) 60 oz/in (65 N/100mm)

Ultimate Dwell (72 Hrs.) 75 oz/in (82 N/100mm)

Adhesion to Polypropylene (PSTC-101)

15 Minute Dwell (Avg.) 60 oz/in (65 N/100mm)

Adhesion to Textured ABS (PSTC-101)

15 Minute Dwell (Avg.) 37 oz/in (40 N/100mm)

Adhesion to Glass (PSTC-101)

15 Minute Dwell (Avg.) 82 oz/in (90 N/100mm)

Abrasion Resistance (ASTM D4060):

CS-10 Wheels, 500g wts.

Material withstands up to 3700 cycles

Gloss (20°):

60° 50 Gardner Units minimum

Minimum Application Temperature

0°F (-18°C)

Service Temperature

-40°F to 180°F (-40°C to 82°C)

Average Outdoor Durability:

Not recommended for outdoor use.

Chemical Resistance:

REAGENT	7 DAY IMMERSION	DIP TEST
30% Sulfuric Acid	NE	NE
10% Sulfuric Acid	NE	NE
30% Hydrochloric Acid	NE	NE
10% Hydrochloric Acid	NE	NE
Glacial Acetic Acid	F	F
5% Acetic Acid	NE	NE
50% Sodium Hydroxide	NE	NE
10% Sodium Hydroxide	NE	NE
10% Ammonia	NE	NE
5% Sodium Hypochlorite	NE	NE
10% Sodium Chloride	NE	NE
MEK	F	F
Acetone	F	F
Toluene	F	F
Methanol	NE	NE
Isopropyl Alcohol	NE	NE
Heptane	F	NE
Mineral Spirits	NE	NE
Turpentine	F	NE
Diesel Fuel	NE	NE
Kerosene	NE	NE
Gasoline	F	F
ASTM #3 Oil	NE	NE
SAE 20 Oil	NE	NE
Alconox®	NE	NE

NE = No Effect

F = Failed (affected sample)

Dip Test: Five 10 minute dips in reagent with 30-minute recovery.

7 Day Immersion Test: Immersed in the reagent for 7 days.

Shelf life is two years from the date of receipt for this product as long as this product is stored in its original packaging

in an environment below 80° F (27° C) and 60% RH. It remains the responsibility of the user to assess the risk of using this product. We encourage customers to develop testing protocols that will qualify a product's fitness for use in their actual application.

Trademarks:

ASTM: American Society for Testing and Materials (U.S.A.)

Alconox® is a registered trademark of Alconox Co.

All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units

PSTC: Pressure Sensitive Tape Council (U.S.A.)

SAE: Society of Automotive Engineers

Note: All values shown are averages and should not be used for specification purposes.

Test data and test results contained in this document are for general information only and shall not be relied upon by Brady customers for designs and specifications, or be relied on as meeting specified performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact Brady for further information.

Product compliance information is based upon information provided by suppliers of the raw materials used by Brady to manufacture this product or based on results of testing using recognized analytical methods performed by a third party, independent laboratory. As such, Brady makes no independent representations or warranties, express or implied, and assumes no liability in connection with the use of this information.

WARRANTY

Brady products are sold with the understanding that the buyers will test them in actual use and determine for themselves their adaptability to their intended uses. Brady warrants to the buyers that its products are free from defects in material and workmanship but limits its obligation under this warranty to replacement of the product shown to Brady's satisfaction to have been defective at the time Brady sold it. This warranty does not extend to any persons obtaining the product from the buyers. This warranty is in lieu of any other warranty, express or implied, including, but not limited to, any implied warranty of merchantability or fitness for a particular purpose, and of any other obligations or liability on Brady's part. Under no circumstances will Brady be liable for any loss, damage, expense, or consequential damages of any kind arising in connection with the use, or inability to use Brady's products.

Copyright 2020 Brady Worldwide, Inc. | All Rights Reserved
Material may not be reproduced or distributed in any form without written permission.